

口罩过滤材料

Face Mask Media

材料可覆盖的口罩类别

Types of Masks That the Material Can Cover



口罩 Mask	口罩标准 Mask Standards	克重范围(g/m ²) Weight Range (g/m ²)	口罩等级 Mask Grade	过滤性能测试条件 Filtration Performance Test Conditions
中国_医用防护口罩	GB 19083-2010	25~50	1级(≥95%) 2级(≥99%) 3级(≥99.97%)	85L/min, 0.3um, 2%NaCl
中国_医用外科口罩	YY 0469-2011	20~30	BEF≥95%	32L/min, 0.3um, 2%NaCl
中国_日常防护口罩	GB/T 32610-2016	45~60	A级(≥99%) B级(≥95%) C级(≥90%) D级(≥80%)	85L/min, 0.3um, 2%NaCl & 石蜡油
中国_KN95口罩	GB 2626-2019	50~80	KN90(≥90%) KN95(≥95%) KN100(≥99.97%)	85L/min, 0.3um, 2%NaCl & 石蜡油
美国_N95口罩	42 CFR Part 84	50~80	N95(≥95%) N99(≥99%) N100(≥99.97%)	85L/min, 0.3um, 2%NaCl
美国_医用外科口罩	ASTM F2100-2019	25~30	Level1(BFE≥95%) Level2(BFE≥98%) Level3(BFE≥98%)	32L/min, 0.1um, 2%NaCl
欧盟_FFP系列口罩	EN 149:2001+A1:2009	40~60	FFP1(≥80%) FFP2(≥94%) FFP3(≥99%)	95L/min, 0.3um, Paraffin oil
欧盟_医用口罩	EN 14683:2019	25~50	Type I(BFE≥95%) Type II(BFE≥98%) Type III(防喷溅)	金黄色葡萄球菌悬浮液
日本_防尘口罩	JIS T 8151:2018	25~50	DS1(≥80%) DS2(≥95%) DS3(≥99.9%)	85L/min, 0.3um, 2%NaCl
韩国_KF系列口罩	KMOEL-2017-64	25~50	KF80(≥80%) KF94(≥94%) KF99(≥99%)	85L/min, 0.3um, 2%NaCl

口罩合作品牌

Cooperative Mask Brand

